



**Retail systems Fire ratings - Aug. 2008**

The following are results of the ASTM E84 standard method for test for surface burning characteristics of building materials. Copies of complete test results are available upon request.

Note: Flame spread dictates class:  
 I or A : 0-25  
 II or B : 26-75  
 III or C : 76-200

Surface tested	Class			Flame Spread			Smoke Developed		
	<u>Displawall</u>	<u>Displawall</u>		<u>Displawall</u>	<u>Displawall</u>		<u>Displawall</u>	<u>Displawall</u>	
	<u>Non-inserted</u>	<u>Aluminum insert</u>	<u>Visplay Holder</u>	<u>Non-inserted</u>	<u>Aluminum insert</u>	<u>Visplay Holder</u>	<u>Non-inserted</u>	<u>Aluminum insert</u>	<u>Visplay Holder</u>
Paint Grade	C	B	N/A	115	70	N/A	80	90	N/A
Painted	C	C	N/A	115	105	N/A	200	95	N/A
LPM	C	C	N/A	190	160	N/A	80	95	N/A
HPL	C	C	B	95	95	60	125	90	190
FR Core & Std HPL	N/A	A	N/A	N/A	20	N/A	N/A	35	N/A
FR Core & FR HPL	N/A	A	A	N/A	20	15	N/A	85	115

**N/A indicates that product was not tested**

This information supersedes all data previously published

\*\* Note: the use of fire rated core will reduce the load capacity of the system. You will need to determine if it meets your needs.

Visplay holders tested: Mono 55, Mono 40, Mono R30, Mono 25, Mono 12, Stripes Mono, Beam Mono, Invs 6 Mono, Xero, Stripes profile



Dover, Ohio 44622 800-377-1221  
 www.marlite.com-info@marlite.com