

SUBJECT: CHEMICAL RESISTANCE

PRODUCT: FIBERGLASS/POLYESTER LINER PANEL 1200TOS

PROCEDURE: Tests in accordance with the requirements of ASTM D-543. Samples completely immersed on the chemicals for seven (7) days at 73°F. The following information is offered as a general guideline only and should not be considered as guarantee of performance.

<u>Recommended for Prolonged Exposure to:</u>	<u>Recommended for Intermittent Exposure To:</u>	<u>Not Recommended for Prolonged Exposure To:</u>
Acetic Acid 5%	Ammonium Hydroxide 10%	Acetone
Carbon Tetrachloride	Ethyl Alcohol	Ethyl Acetate
Citric Acid 10%	Hydrachloric Acid 10%	Ethylene Dichloride
Cutting Oil (Commercial Grade)	Nitric Acid 10%	Methylene Chloride
Distilled Water	Phenol Solution 5%	
n-Heptane	Sodium Hydroxide 1%	
Hydrogen peroxide 5%	Sodium Hydroxide 10%	
Hydrogen Sulfide	Gasoline (Red)	
Isopropyl Alcohol 50%	Sulfuric Acid 3%	
Oleic Acid C.P.	Sulfuric Acid 30%	
Sodium Carbonate 2%	Toluene	
Sodium Chloride 19%		
Sulfur Dioxide		

"DISCLAIMER AND LIMITATION OF LIABILITY"

Since Seller exercises no control over Buyer's application or use of the product manufactured by Seller ("products") and since materials used with the products may vary. It is understood that:

(a) THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE.

(b) While all data presented in Seller's technical data sheets is based on the best information available to Seller and believed correct, such data is not to be construed as a warranty that the products will conform to such specifications. Such technical data sheets are subject to change without notice.

(c) The liability of the Seller shall not exceed the purchase price of the products and the Buyer shall not be entitled to nor Seller be liable for any consequential, incidental, indirect or special damages resulting in any manner from the furnishing of the product or for any damages of any kind arising from the use of the products.